

Product Description

D-A ProLith[™] is a general purpose lithium grease formulated for excellent mobility and pumping ease in centralized lubrication systems. ProLith No. 2 grade offers better low temperature grease delivery to critical lubrication points than most No. 1 grades. The red color makes this grease easy to identify during application and operation. The combination of EP (extreme pressure) additives and a stable soap structure results in a high quality grease capable of protecting heavily loaded machinery, while remaining in place.

Product Features and Benefits

Special blend of extreme pressure additives limits wear and reduces friction in normal and severe machine service.
Rust and corrosion preventatives protect both ferrous and non-ferrous metals in damp or corrosive environments.
Red color makes ProLith[™] easy to identify during application and operation.
Good shear stability and bleed resistance protect against grease leakage and help control lubrication costs.
Pumps easily from tubes and other types of containers, perfect for use in central lubrication systems or in all weather conditions.

PRODUCT AT A GLANCE

- Lithium
- Does not contain Moly
- Red Color
- Multi-Purpose
- Excellent mobility in centralized lubrication systems



D-A Lubricant Company, Inc.

801 Edwards Drive, Lebanon, IN 46052 • TEL: 317.923.5321 • FAX: 765.482.3065 • EMAIL: dalube@dalube.com
www.dalube.com



Supports the Performance Requirements of:

General Lubrication
Bearings
Track Rollers
Drive Rollers
Fittings

Pivot Pins
5th Wheel Applications
Semi-Trailer Landing Gears
Semi-Trailer Wheel Axle Bearings

Typical Properties

Property	ASTM	#000	#00	#0	#1	#2
NLGI Grade	D217	#000	#00	#0	#1	#2
Color	Visual	Red	Red	Red	Red	Red
Soap Type	D128	Lithium 12 - Hydroxystearate				
Penetration, Worked 60 @ 77° F	D217	445 - 475	400 - 430	355 - 385	310 - 340	265 - 295
Dropping (Melting) Point, °F (°C)	D2265	320 (160)	330 (166)	340 (171)	350 (177)	365 (185)
Base Oil Viscosity @ 40° C	D445	320	250	250	250	250
4-Ball Weld Load, kg	D2596	315	315	315	315	315
4-Ball Wear Scar Diameter, mm	D2266	<0.6	0.5	0.5	0.5	0.5
Timken OK Load	D2509	40	35	35	35	35
Bearing Rust Test	D1743	Pass	Pass	Pass	Pass	Pass
Copper Corrosion Test	D4048	1b	1b	1b	1b	1b
Molybdenum Disulfide, wt. %	D128	None	None	None	None	None
D-A Part Numbers	Drum - 400 lb	*	12532	12522	12502	12512
	Quarter Drum - 120 lb	*	12536	12526	12506	12516
	Pail - 35 lb	11038	12538	12528	12508	12518
	Cartridges - 50/case	*	*	*	12507T	12517T

*Special order. Minimums will apply. Extended delivery time needed.

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture. The information contained herein is subject to change without notice.

To Order D-A Products, Call 1-800-OIL-LUBE (1-800-645-5823) or Fax orders to 765-482-3065

D-A Lubricant Company, Inc.

801 Edwards Drive, Lebanon, IN 46052 • TEL: 317.923.5321 • FAX: 765.482.3065

Email: dalube@dalube.com • www.dalube.com

