

**WearGuard™ D-A SYN 3000 Series** is a premium Group III synthetic blended fluid formulated with **ChemGuard™** additive technology system. It is designed to exceed the demanding lubrication requirements of oil flooded rotary vane, screw and reciprocating type compressors. **WearGuard™ D-A SYN 3000 Series** conforms to ISO viscosity classifications 32, 46, 68, 100 and 150. It is formulated from severely hydro-treated, hydro-cracked hydrocarbon base stocks combined with the latest developments in additive technology. This combination makes **WearGuard™ D-A SYN 3000 Series** excellent for oxidation and thermal degradation resistance - providing the potential for extended drain intervals, fewer air filter changes and less oil carryover.

## Applications

- Oil Flooded Rotary Vane Compressors
- Oil Flooded Screw Type Compressors
- Air Compressors where the lubricant is injected directly into the airstream
- Reciprocating (Piston-Type) Compressors (ISO 100 grade)
- Vacuum Pumps

## Characteristics

- Low temperature fluidity
- Exceptional oxidation stability
- Excellent anti-friction and anti-wear properties
- D-A synthetic base oil combination is compatible with seals and elastomers commonly found in compressed air systems
- Excellent demulsibility protects against rust and corrosion

## Typical Properties

WearGuard™ D-A SYN 3000 Series	ASTM Method	WearGuard D-A SYN 3032	WearGuard D-A SYN 3046	WearGuard D-A SYN 3068	WearGuard D-A SYN 3100	WearGuard D-A SYN 3150
ISO Viscosity Grade	D2422	32	46	68	100	150
SAE Viscosity Grade		10	20	30	40	50
Viscosity, cSt @						
@ 100°C	D445	5.8	7.8	10.0	14.1	20.4
@ 40°C	D445	32.8	45.6	67.9	101.2	156.7
Viscosity Index	D2270	127	126	131	142	150
Pour Point °C (°F)	D97	-34 (-29)	-29 (-20)	-24 (-11)	-24 (-11)	-24 (-11)
Flash Point °C (°F)	D92	230 (446)	248 (478)	250 (482)	252 (486)	255 (491)
Rust	D665B	Pass	Pass	Pass	Pass	Pass
Demulsibility, min.	D1401	5	5	10	10	15
Foam, Sequence I, II, III	D892	0/0	0/0	0/0	0/0	0/0
FGZ Wear	D5182	+12	+12	+12	+12	+12
API Gravity, 60/60°F	D287	35.6	34.8	34.5	34.2	34.0
Copper Corrosion	D130	1b	1b	1b	1b	1b
Carbon Residue, mg.		<0.1	<0.1	<0.1	<0.1	<0.1



801 Edwards Drive Lebanon, IN 46052  
 1-800-OIL-LUBE (1-800-645-5823)  
 (317) 923-5321 (765) 482-3065 FAX  
[www.dalube.com](http://www.dalube.com) [dalube@dalube.com](mailto:dalube@dalube.com)

DA-SCO3000 rev 11/15 new 7/2011

The information in this bulletin is, to the best of our knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

© 2015, D-A Lubricant Company, Inc.

Made in  
USA